



Technical Data Sheet

Quality Specification

Palm Kraft plus

	Basis Weight	Bursting Strength	Burst Index	SCT, CD	SCT, CD
Dimension	[g/m ²]	[kPa]	[kPa m ² /g]	[kN/m]	[kN/m]
Standard	ISO 536	ISO 2759	ISO 2759	ISO 9895	ISO 9895
Tolerance	± 3 %	Minimum per Reel	Minimum per Reel	Average per Delivery	Minimum per Reel
	115	345	3.0	2.45	2.35
	130	390	3.0	2.8	2.6
	150	450	3.0	3.1	2.9
	170	510	3.0	3.4	3.2
	180	540	3.0	3.5	3.3

Preconditioning: ISO 187, 23°C, 50 % relative humidity

Moisture: 6.5 - 9 %

Sizing: Cobb1800 < 100 g/m²

Issue date 1 January 2024